




Plasmor Ltd
Womersley Road, Knottingley
West Yorkshire, WF11 0DL

BS EN 771-3 (2011 + A1:2015)

Bison PM 140 WIDE T Block 3.6N/mm² BISONPM140W

Loadbearing and non-loadbearing applications in all forms of walling including single leaf, cavity and partitions.

Dimensions (mm)	530 / 485 x 140 x 140
Dimensional Tolerances:	Category D1
Configuration:	Solid
Compressive Strength:	3.6N/mm ²
Dimensional Stability:	=< 0.60mm/m
Shear Bond Strength:	0.15N/mm ²
Flexural Bond Strength:	NPD
Reaction to Fire:	Euro Class A1
Water Absorption:	NPD
Water Vapour diffusion coefficient:	5/15
Gross Dry Density:	850 kg /m ³
Configuration:	Group 1 Solid
Thermal Conductivity	0.24 W/m.K (λ_{10} , dry, mat P = 50%)
Durability against freeze-thaw:	Not to be left exposed



See also Declaration of Performance BISONPM140W

technical@plasmor.co.uk